

# PolymerTop

# Delosh

Concrete Refinement Products

Fine blend of polymers that leaves a higher topical build on the polished or troweled concrete surface. By burnishing to heat cure, a highly protective top cap is created providing an immense stain resistance while maintaining a vapor transmissible slab.

## Applicator Tips

PolymerTop is best applied to a clean, dry substrate. No humidity should be left in slab.

Do not burnish until fully dried to touch and no dusting (white lines when dragging fingers across surface).

Two, thin applications is always better than one heavy application. Less is more when applying acrylic guards. Always.

In best practice to help disguise surface defects, put excessive pressure on applicator pad when going over said defects. The goal is to force defect to absorb material in multiple passes. Be sure to not puddle defects.

Burnishing with a heat pad or diamond impregnated pads is strictly not recommended. Overheating of this high solids topical guard will quickly cause buildup on the pad and immediately put visible scratches in the guard surface.

In case of buildup on burnisher pad causing visible scratches, re-mediate as follows:

- Replace with less abrasive pad such as a white or aqua polishing pad. Even regular hogs hair pads may be too abrasive and cause excessive heat due to the relation between the substrates' porosity and amount of topical acrylic sitting atop surface.

- Re-burnish affected (scratched) areas of floor. Typically, immediate results of removing scratches achieved.

- In scenarios where heavy gouges occurred due to not initially noting the guard buildup, reapplication of guard in affected area may be necessary. Then proceed to re-burnish.

**Best Burnishing Procedure:** Using a medium to soft hogs hair pad (soft white or aqua pad for denser slabs), slowly burnish the PolymerTop. The initial burnish pass will note increased gloss but likely leave a gloss 'trail' where each parallel pass is performed and visibly notable. Therefore it is recommended to burnish a second time, crosshatching the burnishing operation to reduce burnish lines and achieve full hardening of the stain protectant. Any remaining burnish and product application lines that become apparent during the burnishing procedure will typically lose visibility after product fully cures; said marks are the humidity from the heating of the product on the substrate.

Do not wash floor for 72 hours to avoid adding moisture to a curing sealer.

**Further Increasing Gloss:** Burnishing in-between coats substantially increases final gloss & clarity. Also, once initial burnishing operation is performed, burnishing again 2-4 weeks later substantially increases gloss.

## Further Operations Questions?

Email [support@deloshconcretepolishing.com](mailto:support@deloshconcretepolishing.com) or contact your Delosh Representative

[deloshconcretepolishing.com](http://deloshconcretepolishing.com)